



INDIANA

TEST, CALIBRATION & CERTIFICATION SERVICES

7.8 QF-02
REV 00



TC-5982

TEST REPORT

ULR : TC598224000011068F	REPORTS NO: C/2024/223614	ISSUE DATE: 03.08.2024
CUSTOMER: VEDIKA ENTERPRISES Plot No-246, Phase-IX, Indl. Area Mohali (Punjab)	LSRF NO-71360	RECEIPT DATE: 26.07.2024
CUST.REF. NO: Letter Dated: 26.07.2024	SAMPLE NO(S): ONE	TEST DATE(S): 30.07.2024 to 03.08.2024
SAMPLE DRAWN BY: CUSTOMER	SAMPLE CONDITION: Rectangular Test Piece	TEST METHOD: ASTM B-117-2019
SAMPLE DESC: Copper Tube +S.S. Metal		SAMPLING PROTOCOL: ---
		PAGE NO (S): 01 OF 01

DISCIPLINE: Chemical Testing

GROUP: Corrosion Test

Sample ID: C-234310

Salt Spray Test Result

Observation: No red rust visible at the end of 96hrs of testing.

Condition:	1. Salt Solution (NaCl)	50g/l±10%
	2. Temperature	35 ± 2°C
	3. pH Value	6.5-7.2
	4. Fog Collection	1-2 ml/hours in 80cm ² Area
	5. Duration	96 Hours



Shashi Pal
Analyst
Shashi Pal

G.D. Singh
C.P.O/V.P.
G.D. Singh/A.P. Singh

A.P. Singh
Authorized Signatory
C.P.O/V.P.
A.P. Singh/G.D. Singh

Sample Not Drawn by Lab. The Results apply to sample as Received. Sample Description Given Is As Described by the Customer.

End of Report

Note: 1. This report refers only to the tested sample and applicable parameter and result reported is valid at the time of and under the stated conditions of measurement. 2. Any complaint about the report should be communicated in writing within 7 days of issue of this report. 3. The sample will be destroyed after one month unless instructed otherwise. 4. Laboratory standards are traceable to national/international standards. 5. This report is not to be reproduced wholly or in part and cannot be used as evidence in a court of law and shall not be used in advertising media without the written permission of ICS. 6. The liability of our laboratory is limited to structural amount. No liability will be accepted after the sample is taken back. 7. The sample description is not verified in all cases and is given "as described" by the customer the sample not drawn by us and analysis conducted on "as received basis" unless specified otherwise. 8. Endorsement of any product's number, inherent implied in the testing pertains only to the sample tested. 9. While "INDIANA" has made their best endeavours to provide accurate and reliable information, "INDIANA" is not responsible for any financial liability due to any act of omission or error made.

Address : D-151, Phase VII, Industrial Area, Mohali (Near Chandigarh) - 160 055 Punjab (India)
Tel.: +91-172-4668151, 5097151 Fax : +91-172-2236518 Email : indianaindia@gmail.com

website : www.indianaindia.co

A division of INDIANA FERRO ALLOYS